Quasistatic stopband in the spectrum of one-dimensional piezoelectric phononic crystal

A.A. Kutsenko, A.L. Shuvalov, and O. Poncelet

Université de Bordeaux, CNRS, UMR 5295,

Institut de Mécanique et d'Ingénierie de Bordeaux, Talence 33405, France

A. N. Darinskii

Institute of Crystallography RAS, 119333 MOSCOW, RUSSIA

(Dated: March 24, 2015)

arXiv:1410.7215v2 [math-ph] 23 Mar 2015

Abstract

Propagation of a longitudinal wave through the periodic structure composed of alternating elastic and piezoelectric layers is considered. The faces of each piezoelectric layer are electroded and connected via a circuit with the capacity C. It is shown that if $C < 0$ then the Floquet-Bloch spectrum $\omega(K)$ in a certain range of negative C may possess a quasistatic absolute stopband starting at $\omega = 0$. Other unusual features of the spectrum occurring at certain fixed values of $C < 0$ are the infinite group velocity of the first branch at the origin point $\omega = 0$, $K = 0$ and the flat bands $\omega = \text{const}$.

I. INTRODUCTION

A periodic structure composed of alternating elastic and piezoelectric layers, where the faces of each piezoelectric layer are electroded and connected by a circuit with the capacity C, has been considered in [1, 2]. The dispersion equation for a bilayered unit cell has been obtained in [1] and generalized for a multilayered unit cell in [2]. The tunable via C effective constants of the periodic structure were derived in [2]. It has been noted in [1] that the capacity C of the external circuit may be negative. The present paper analyzes some unusual features of the Floquet-Bloch dispersion spectrum occurring at $C < 0$. In such a case, using the definition of the quasistatic effective elastic constant c^0_{eff} [2], it is shown that the most interesting behavior comes about at low frequency. This is because the value of c^0_{eff} becomes negative in the certain interval of $C < 0$, where c^0_{eff} varies from $-\infty$ to zero. As a result, at $c^0_{\text{eff}} < 0$ there occurs an absolute stopband which starts from the quasistatic limit $\omega = 0$, while the first dispersion branch starts from nonzero ω. At certain negative C, the group velocity of this branch changes from positive to negative value. Other peculiar features are infinite group velocity at the origin $\omega = 0,\ K = 0$ of the first dispersion branch at the pole $c^0_{\text{eff}} \to +\infty$ and a flat band $\omega = 0$ at $c^0_{\text{eff}} = 0$.

II. BACKGROUND

Consider a periodic structure whose unit cell consists of elastic layer 1 and piezoelectric layer 2. Suppose that the faces of each piezoelectric layer are electroded and connected by a circuit with capacity C. Let a time-harmonic longitudinal wave propagate along the axis X_3 orthogonal to the layer interfaces. Denote the density and elastic constant of the elastic layer by ρ_1 and $c_{33} = c_1$, and the density and elastic, piezoelectric and dielectric constants of the piezoelectric layer by ρ_2, $c^E_{33} \equiv c^E$, $c^D_{33} \equiv c^D = c^E + e^2/\varepsilon$, $e_{33} \equiv e$, $\varepsilon_{33} \equiv \varepsilon$. The layer thicknesses are d_1 and d_2 so that the period is $T = d_1 + d_2$. The displacement $u_3 \equiv u$ and stress $\sigma_{33} \equiv \sigma$ at the period edges $x_3 = 0$ and $x_3 = T$ are related as follows [2]

$$\begin{pmatrix} u(T) \\ \sigma(T) \end{pmatrix} = \mathbf{m}_2\mathbf{m}_1 \begin{pmatrix} u(0) \\ \sigma(0) \end{pmatrix} \tag{1}$$

with

$$\mathbf{m}_1 = \mathbf{m}_{10}, \quad \mathbf{m}_2 = \mathbf{m}_{20} + \frac{1}{\frac{S}{C} - M_3} \begin{pmatrix} M_1 \\ M_2 \end{pmatrix} \begin{pmatrix} M_2 \\ M_1 \end{pmatrix}^\top,$$

$$\mathbf{m}_{j0} = \begin{pmatrix} \cos k_j d_j & \frac{\sin k_j d_j}{Z_j \omega} \\ -Z_j \omega \sin k_j d_j & \cos k_j d_j \end{pmatrix}, \quad j = 1, 2. \tag{2}$$

where S is the surface area of the electrode, $^\top$ means transposition and

$$M_1 = \frac{h \sin k_2 d_2}{Z_2 \omega}, \; M_2 = h(\cos k_2 d_2 - 1),$$
$$M_3 = h M_1 - \frac{d_2}{\varepsilon}, \quad k_1 = \omega \sqrt{\frac{\rho_1}{c_1}}, \quad k_2 = \omega \sqrt{\frac{\rho_2}{c_2^D}},$$
$$h = \frac{e}{\varepsilon}, \quad Z_1 = \sqrt{\rho_1 c_1}, \quad Z_2 = \sqrt{\rho_2 c_2^D}. \tag{3}$$

In view of (1), the dispersion equation of the Floquet-Bloch spectrum $\omega(K)$ is

$$\cos KT = \frac{1}{2} \text{trace } (\mathbf{m}_2 \mathbf{m}_1), \tag{4}$$

where K is the Floquet wavenumber. According to [2], taking low-frequency asymptotics yields the quasistatic effective elastic constant and effective density of the periodic structure in the form of

$$\frac{T}{c_{\text{eff}}} = \frac{d_1}{c_1} + d_2 \left(c_2^E + \frac{e^2}{\frac{C d_2}{S} + \varepsilon} \right)^{-1}, \qquad T \rho_{\text{eff}} = d_1 \rho_1 + d_2 \rho_2. \tag{5}$$

The corresponding quasistatic effective speed is

$$\lim_{K \to 0} \frac{\omega}{K} = \sqrt{\frac{c_{\text{eff}}}{\rho_{\text{eff}}}}. \tag{6}$$

Our purpose is to analyze the dispersion spectrum and its low-frequency limit in the case $C < 0$.

III. EXAMPLE

Following [1], consider an example of the glass/PZT periodically bilayered structure where each PZT layer is electroded and connected as in the inset to Fig. 1. Let $d_1 = d_2 = 1$ mm. The material constants are given in [1]. The dependence (5) of the quasistatic effective



FIG. 1. Dependence of the quasistatic effective elastic constant c^0_{eff} on the external capacity C for the glass / PZT periodically bilayered structure where each PZT layer is electroded and connected.

elastic constant c^0_{eff} on C is plotted in Fig. 1. It is seen that c^0_{eff} is negative for $\frac{C}{S} \in (\frac{C_\infty}{S}, \frac{C_0}{S})$ where

$$\frac{C_\infty}{S} = -\frac{e^2 d_1}{(c_1^E d_2 + c_2^E d_1) d_2} - \frac{\varepsilon}{d_2}, \qquad \frac{C_0}{S} = -\frac{e^2}{d_2 c_2^E} - \frac{\varepsilon}{d_2} \tag{7}$$

are pole and zero of $c^0_{\text{eff}}(\frac{C}{S})$. This leads to a quasistatic absolute stopband which starts from $\omega = 0$ and extends to a certain nonzero ω.

Let us examine in detail the evolution of the dispersion spectrum with the decrease of $C < 0$. Figure 2 displays a set of dispersion spectra at different fixed values of $C < 0$ which are compared with the spectrum at $C = 0$. It is seen that the values $\frac{C}{S} \in (\frac{C_\infty}{S}, 0)$ first affect the second branch $\omega(K)$ which changes the slope from negative to positive. As $\frac{C}{S}$ approaches $\frac{C_\infty}{S} \approx 10.67\ \frac{\mu\text{F}}{\text{m}^2}$, the group velocity $d\omega/dK$ of the first branch at the origin point $\omega = 0,\ K = 0$ tends to infinity (along with the quasistatic phase velocity (6)). This implies stiffening effect which can be observed in [1]. In the interval $\frac{C}{S} \in (\frac{C_\infty}{S}, \frac{C_0}{S})$, where $c^0_{\text{eff}} < 0$ (see Fig. 1), there is the absolute stopband starting from the quasistatic limit $\omega = 0$. At certain $\frac{C}{S} \in (\frac{C_\infty}{S}, \frac{C_0}{S})$, the first branch which starts from $\omega \neq 0$ becomes flat and then changes slope from positive to negative, see Fig. 2 at $\frac{C}{S} = -11\ \frac{\mu\text{F}}{\text{m}^2}$ and $\frac{C}{S} = -12\ \frac{\mu\text{F}}{\text{m}^2}$. For $\frac{C}{S} < \frac{C_0}{S} \approx 13.3\ \frac{\mu\text{F}}{\text{m}^2}$ the quasistatic elastic constant c^0_{eff} and hence the quasistatic

phase velocity begin to grow from zero, so that the first dispersion branch reappears at its quasistatic origin $\omega = 0,\ K = 0$. Further decrease of C affects the position of the first stopband, as it is observed in Fig. 2 for $\frac{C}{S} = -14\ \frac{\mu\mathrm{F}}{\mathrm{m}^2}$, ..., $-40\ \frac{\mu\mathrm{F}}{\mathrm{m}^2}$.



FIG. 2. Dispersion curves for the glass/PZT periodically bilayered structure (see inset in Fig. 1) for different negative capacities C (black lines) in comparison with the spectrum for $C = 0$ (grey lines).

IV. CONCLUSIONS

A possibility has been shown of the quasistatic absolute stopband, the infinite group velocity and the flat bands in the Floquet-Bloch spectrum of a periodic structure of elastic and piezoelectric layers where the faces of each piezoelectric layer are electroded and connected via a circuit with negative capacity C.

ACKNOWLEDGMENTS

This work has been conducted in the framework of the project MIRAGES ANR-12-BS09-0015 with the support of the competitiveness cluster Aerospace Valley. The authors grateful to A.-C. Hladky and B. Dubus for the useful discussions.

---

[1] S. Degraeve, C. Granger, B. Dubus, J.O. Vasseur, A.-C. Hladky, M. Pham-Thi. "Contrôle électrique de la propagation d'ondes èlastiques dans des cristaux phononiques piézoelectriques" 21 Congrés Francais de Mècanique. Bordeaux. 26-30 August, 2013. http://documents.irevues.inist.fr/handle/2042/52155

[2] A.A. Kutsenko, A.L. Shuvalov, O.Poncelet, A.N. Darinskii. Tunable effective constants of the one-dimensional piezoelectric phononic crystal. Submitted. (see arxiv)